

---

Subject: Anode Wire Quality

Posted by [Christian Lippmann](#) on Tue, 18 May 2004 14:42:32 GMT

[View Forum Message](#) <> [Reply to Message](#)

---

Hi everybody,

since one is only allowed to attach three files the anode wire images are in this topic:

TW015: A bad quality wire. The gold palting has fallen of in places.

TW025: Also not very nice.

TW031: A good wire.

Here are the images. In case you can not view them (under windows) you need to save them to your disk. Then they can be viewed.

---

#### File Attachments

- 1) [TW015-2.TIF](#), downloaded 1019 times
  - 2) [TW025-4.TIF](#), downloaded 1025 times
  - 3) [TW031-4.TIF](#), downloaded 1064 times
- 

---

Subject: Re: Anode Wire Quality

Posted by [Clemens Adler](#) on Mon, 13 Sep 2004 10:14:44 GMT

[View Forum Message](#) <> [Reply to Message](#)

---

Hello everybody,

Oleg reported that the anode wire is producing a lot of dust during winding on the meteor, much more than to his experience is normal. I looked on our meteor and also found quite some gold dust (see some pictures at [http://www.physi.uni-heidelberg.de/~adler/TRD/pics/2004\\_09\\_10/](http://www.physi.uni-heidelberg.de/~adler/TRD/pics/2004_09_10/) ). This amount is from one Anode winding (Andrea cleaned everything before the last winding).

What is the opinon of the experts on this? can it be that this wire is bad quality?

cheers,  
Clemens

---

---

Subject: Re: Anode Wire Quality

Posted by [Clemens Adler](#) on Tue, 14 Dec 2004 10:15:17 GMT

[View Forum Message](#) <> [Reply to Message](#)

---

Hello everybody,

After Oleg reported some time ago that he feels that the anode wire we're using is producing an surprising amount of gold dust compared to other wire he used. I now heard from Mihai that they discovered that on large portions of the anode wire they are using the gold plating is (partially) missing. I just discussed this with Joerg, but we were both not really sure whether this is a problem. So the question to the experts:

For what is the gold plating needed, except for soldering the wire. And what is the opinion whether anode wire with missing gold plating could be used?

Of course there is still always the question whether gold dust (which as Mihai remarked correctly will also stay on the wire) or gold plating hanging off the wire (which would also be imaginable) would not be nice.

Please respond if you have any experience or opinion. This is becoming a rather urgent issue.

thanks,

Clemens

---

Subject: Re: Anode Wire Quality

Posted by [Clemens Adler](#) on Tue, 11 Jan 2005 15:25:48 GMT

[View Forum Message](#) <> [Reply to Message](#)

---

Hello,

I looked at our anode wire under the electron microscope today. I took a piece of wire before and a piece after winding.

Unfortunately the operator was rather stressed and didn't have a lot of time, so we looked at both pieces simultaneously, i.e. I do not know which one is which.

Since it is only allowed to attach 3 files, I put the pictures under:

<http://www.physi.uni-heidelberg.de/~adler/TRD/pics/>

1st wire:

Anode1.tif (2000x)

Anode1a.tif (4000x)

2nd wire:

(each also with 2000x and 4000x at 2 different places on the wire)

Anode2.tif

Anode3.tif

Anode4.tif

Anode5.tif

Altogether it seems that wire 1 is smoother than the 2nd wire which has those bumps. But I guess it is hard to judge whether this wire was modified by winding, or whether the differences are just because it's a different piece of wire.

cheers,

Clemens